


Room Temperature Data after 16 years

TOSHIBA Logistics Corp

Application Date: August, 1996 Area: 16,500sq.m. (Metal Roof)
Measurement Date: 24 July, 2012 (13:00 Ambient temp: 35.6°C)

It still maintains the same room temperature and effect after 16 years.

Only top coat has been applied after 12 years, and room temperature has dropped in addition. Surface temperature was measured 37°C~38°C.



<Surface Temperature>



	Outside Temperature	Room Temperature
BEFORE (1994)	35.5°C	39.2°C
AFTER (1994)	35.5°C	32.9°C
After 10 years (2006)	35°C	33°C
Top Coat was applied in 2008		
After 16 years (2012)	35.6°C	31°C

