



EAGLE
SPECIALIZED
COATINGS
AND
PROTECTED
ENVIRONMENTS

A Division of DW Pearce Enterprises Ltd . (1979)

SafeCoat[®] Latex Intumescent Coating

PRODUCT DESCRIPTION

SafeCoat Latex Intumescent Coating is a single component latex, intumescent fire retardant coating ideally suited for interior applications on various combustible substrates including SPF Plywood (Spruce/Pine/Fir), Oriented Strand Board (OSB), wood trusses and rough stud construction, where Flame Spread Ratings of 25 or less ("Class A" or Class 1) and low Smoke Developed Ratings are required. It limits flame spread by expanding to many times the original dry film thickness when exposed to heat. This expanded material forms a char which insulates the substrate against heat, and reduces available oxygen to the surface. Provides a "Class A" Flame Spread rating of 25 or less as tested under ASTM E84 and CAN4-S102 standards.

USES

imparts a Class A Flame Spread Rating to dimensional lumber, plywood and Oriented Strand Board (OSB).

acts as a thermal barrier to protect foamed plastic insulation when used in conjunction with OSB.

used in lieu of drywall on plywood and OSB for greater strength and resilience.

replaces sprinklers in combustible concealed spaces, under NFPA-13.

can be applied as a mandatory upgrade to assist owners and property managers to meet the latest fire and building code requirements. It may also be applied as a voluntary upgrade to lower fire risks and reduce insurance costs.

FEATURES

- ▽ is non-toxic. It contains no asbestos, harmful ingredients or solvents.
- is cost-effective. A single coat applied at 150 ft²/USG achieves a "Class A" Flame Spread Rating.
- ▲ is fire-resistant. It will not burn in liquid or solid state. Under fire conditions, it forms a char, preventing the spread of flames, and slowing the penetration of heat through the substrate (Fire Endurance).

TECHNICAL DATA and PROPERTIES

Coating Type	Latex
Finish	White, flat finish
Color	Standard: White Optional: Black
Tinting	May be tinted. Use standard latex or universal colorants. Do not exceed 26 mL of tint per liter of SafeCoat Latex.
Specific Gravity	10.9 lbs/US Gallon or 1.30 g/mL
Solids by Weight	58%
Solids by Volume	47%
VOC	25 g/l 0.2 lbs/USG
Dry Time	Touch: 30 min. to 1 hour (varies with temperature and humidity) Recoat: 1 to 2 hours Full cure: 48 hours
Film Thickness	<u>Wood</u> Wet: 10.7 mils Dry: 5.0 mils <u>Foam</u> Wet: 21 mils Dry: 10 mils
Flash Point	No Flash
Storage Limits	Keep from freezing (above 50° F recommended)
Shelf Life	24 months
Packaging	Available in one, five and fifty US gallon quantities

INSTRUCTIONS FOR USE

Surface Preparation:

All surface preparation should be carried out in accordance with good painting practices. Remove all loose, peeling or powdery paint from the surface. All dirt, grease, oil, wax and other foreign material must be removed with a suitable cleaner and allowed to thoroughly dry. Repair all cracks, holes and surface imperfections. All smooth or glossy surfaces should be dulled with sandpaper. New wood surfaces which will be exposed should be coated with a suitable sealer such as SafeCoat 725 to prevent tannin staining of the SafeCoat Latex topcoat. This is particularly recommended when coating Oriented Strand Board.

Application:

SafeCoat Latex Fire Retardant Coating can be applied by brush, roller or airless spray. Airless equipment is most desirable. Use Graco Model 450 or larger or other long-stroke piston type units. Alternatives include gravity fed "Hero" or other diaphragm units. Use a 16 to 21 thousand aperture, with a 12" fan for optimum results. Apply uniformly to entire surface. If thinning is required use clean water only and do not exceed 200 mL per gallon. Surface and ambient temperature must be maintained at greater than 50°F (10°C) during application and must remain so for at least 48 hours following the application. SafeCoat Latex is intended for interior use only. If the coated substrate will be subject to repeated washing or prolonged contact with moisture a finish coat of SafeCoat 725 is recommended. Please note that the addition of any finishing coat will affect the flame spread rating and smoke developed classification. Before applying any finishing coat consult the manufacturer or their representative. A wet film thickness gauge can be used at the start of the application to check that sufficient SafeCoat Latex has been applied. At an application rate of 150 ft²/USG the wet film thickness should be 10.7 mil and will yield a dry film thickness of 5.0 mil. For foam, apply at 80 ft²/USG. The application of SafeCoat Latex should be uniform and leave no exposed uncoated surfaces or edges. If the lumber is pre-coated it should be checked after installation to ensure that construction procedures have not created any exposed uncoated areas.

Clean Up:

All application tools can be easily cleaned with water. If product has dried on, use hot soapy water to soften and remove it.

Precautions:

SafeCoat Latex is not "WHMIS" regulated nor is it subject to the "Transportation of Dangerous Goods Act and Regulations". See MSDS for detailed precautions.

IDENTIFICATION and CERTIFICATION

Each container bears a label with the following marks:



TEST RESULTS

FLAME SPREAD INDEX

Testing was conducted in accordance with ASTM E84 and CAN4-S102 "Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies". Following is a summary of the results of those tests.

Material	¹ FSR	² SDC
Douglas Fir Lumber, coated by SafeCoat Latex with a single coat at a rate of 3.7 m ² /L	5	5
S-P-F Plywood coated by SafeCoat Latex with a single coat at a rate of 3.7m ² /L and a single coat of SafeCoat 725 Overcoat at 7.4m ² /L. ³	5	0
Oriented Strand Board 10 mm nominal thickness, coated by SafeCoat Latex with a single coat at a rate of 3.7 m ² /L.	10	10-25
High density polyurethane foam coated with SafeCoat Latex at 80 ft ² /USG	<25	<150

¹FSR - flame spread rating

²SDC - smoke developed classification

³SafeCoat 725 is not a fire retardant but it is used solely to change gloss and scrubability of the SafeCoat Latex

FLAME RESISTANCE RATING

Testing was conducted in accordance with ASTM E-119 "Floor/Open Ceiling Assembly Fire Test" and NFPA 251 "Small Scale Test" by Guardian Fire Testing Laboratories Inc. of Buffalo, NY. Following is a summary of results:

Assembly	Time to Flame-Through
NO GYPSUM	
2" x 10" nominal SPF floor joists, 16" on centre. 3/4" oriented strand board, tongue and groove flooring.	46 minutes, 37 seconds
Underside assembly coated with SafeCoat Latex with 2 coats at a rate of 7.4 m ² /L (300 ft ² /gal) each coat.	

WITH GYPSUM

2" X 10" nominal SPF floor joists, 16" on centre. 3/4" oriented strand board, tongue and groove flooring. Ceiling: 5/8" type X gypsum wallboard. Exposed side of gypsum coated with 2 coats of SafeCoat Latex at a rate of 7.4m²/L (300 ft²/gal) each coat.

¹No flame-through. Test terminated due to heavy smoke.

GUARANTEE/WARRANTY

Recommendations for the use of our products are based on tests carried out at government approved labs. Manufacturer and seller are not responsible for results where the product is used under conditions beyond our control. Under no circumstances will Magna Coatings Technology Inc OR Eagle Specialized Coatings And Protected Enviroments be liable for consequential damages to anyone in excess of the purchase price of the product or services.